



**serviacero**  
comercial

Galvanized Wire



Theoretical Weights Table					
Diameter		Zinc minimum weight per unit area			kg/m
Thickness	inche	mm	Size OZ/FT	III OZ/FT	
5	0.207"	5.25	0.53	1	0.167
6	0.192"	4.87	0.5	1	0.146
7	0.177"	4.49	0.44	0.9	0.124
8	0.162"	4.11	0.35	0.9	0.104
9	0.148"	3.76	0.35	0.9	0.087
10	0.135"	3.42	0.30	0.85	0.072
10 1/2	0.128"	3.25	0.30	0.85	0.065
11	0.120"	3.06	0.30	0.85	0.057
12	0.106"	2.67	0.30	0.80	0.044
12 1/2	0.099"	2.51	0.30	0.80	0.039
13	0.091"	2.31	0.28	0.75	0.033
14	0.080"	2.03	0.25	0.70	0.025
14 1/2	0.076"	1.93	0.25	0.70	0.023
15	0.072"	1.82	0.20	0.65	0.021
15 1/2	0.067"	1.70	0.20	0.65	0.018
16	0.062"	1.58	0.20	0.65	0.015
18	0.0475"	1.21	0.15	0.50	0.009
20	0.0348"	0.86	0.15	0.45	0.005
22	0.0265"	0.67	0.15	0.45	0.003

Coating in galvanized wire class I and class III